

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.

**PCT**WORLD INTELLECTUAL
International Bureau

WO 9603029A1

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A01G 13/02	A1	(11) International Publication Number: WO 96/03029 (43) International Publication Date: 8 February 1996 (08.02.96)
(21) International Application Number: PCT/EP95/02786 (22) International Filing Date: 15 July 1995 (15.07.95) (30) Priority Data: 94111390.4 21 July 1994 (21.07.94) EP (34) Countries for which the regional or international application was filed: AT et al. (71) Applicants (for all designated States except US): MERCK PATENT GMBH [DE/DE]; Frankfurter Strasse 250, D-64293 Darmstadt (DE). HYPLAST N.V. [BE/BE]; St. Lenaartseweg 26, B-2320 Hoogstraten (BE). (72) Inventors; and (75) Inventors/Applicants (for US only): DAPONTE, Tony, Leon, Filip [BE/BE]; Melis Stokellaan 7, B-2050 Antwerpen (BE). VERSCHAEREN, Patrick, Corneel, Mathilde [BE/BE]; Fresialaan 3, B-2960 Brecht (BE). REYNDERS, Peter [DE/DE]; Bessunger Strasse 190, D-64347 Griesheim (DE). WEIGAND, Manfred [DE/DE]; Saarstrasse 5, D-64342 Jugenheim (DE). (74) Common Representative: MERCK PATENT GMBH; Frankfurter Strasse 250, D-64293 Darmstadt (DE).		(81) Designated States: AU, BR, CA, CN, CZ, FI, JP, KR, NO, PL, RU, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: MULTILAYER POLYMERIC BODY WITH INTERFERENCE EFFECT (57) Abstract The invention relates to a multilayer reflective polymeric body of at least first and second diverse generally transparent polymeric materials, arranged in a sufficient member of alternating layers of said first and second polymeric materials such that a definite part of the light incident on said body is reflected, wherein said first and second polymeric materials differ from each other in refractive index by at least about 0.03 for the screening of solar radiation with the aim of influencing plant growth and the morphogeneais.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Multilayer polymeric body with interference effect

5 The present invention relates to a multilayer polymeric film with interference effect. More particularly, the present invention relates to an agricultural film for the screening of solar radiation with the aim of influencing plant growth and the morphogenesis.

10 It is necessary for a controllable growth of plants to set up special light conditions to affect plant growth and morphogenesis. Special light conditions for plant growth, for example, within a greenhouse or under a mulch film include some which are of particular interest. The temperature within the enclosed area as well as the light intensity and the spectral distribution of the incoming light are important factors for the plant growth.

15 Plants in a greenhouse, for example, will not grow so well if the temperature variation between day and night is large due to a big difference in visible light and NIR radiation impact.

20 From this it follows that the plants stay back in growth. Thus, for the photosynthesis in greenhouses the photosynthetically active radiation (PAR) is only desired while other parts of the solar light should be screened because they have mainly a negative influence on the microclimate. Therefore the following objectives have to be achieved: Firstly, the intensive irradiation by sunlight in particular by NIR radiation needs to be screened,
25 in order to avoid too high temperatures within the enclosed area. Secondly, the incoming light beams are to be scattered in order to prevent burnings on plants. Thirdly, heat within the area is to be stored at night.

30 However, in case of mulch films the opposite effect is desired. The PAR should be screened and all other parts of the solar light should be transmitted. Mulch films are used in agriculture to improve the growing conditions of the useful plants and to minimize the use of chemical herbicides.

35

- 2 -

For certain crop growers want to intervene in the plant morphogenesis. Morphogenesis is the influence of environmental factors on the shape and appearance of the plant. One of these factors is the spectral energy distribution.

5

Raviv and Allingham describe in "Plastic Culture", No. 59, September 1989, pp. 3 to 12, that diffuse light is favourable for a steady growth of plants. Furthermore, it turned out that diffuse light has the advantage of a more uniform illumination and that it does not damage the plants as much as direct radiation. Hancock describes in "Plastic Culture", No. 79, 1988, pp. 4 to 14, that special additives in LDPE have a favourable effect on the microclimate in greenhouses because of the generation of diffuse light and the creation of a favourably thermic effect in the greenhouses. Suitable additives are aluminosilicate in the form of kaolin, calcium carbonate, talc and kaolin clay.

10
15

Greenhouses made of glass already fulfil some of the above-mentioned conditions by virtue of the inherent physical properties of inorganic glasses. Furthermore, constructive measures, for example knurled glass or shadow cloth are known.

20

If the enclosing material is plastic, such as, for example, polyethylene, polyethylene/vinyl acetate copolymers, polyvinyl chloride, polycarbonate or polyacrylate, it is much more difficult to meet these requirements. The high transparency of many plastics for IR radiation results in good heat transmission which, in the case of films, is additionally assisted by the low film thickness.

25

A polymethyl methacrylate glazing material for buildings and vehicles containing an interference pigment for the screening of NIR radiation of a wave length between 800 and 1500 nm is disclosed in DE 2,544, 245.

30

35

- 3 -

The pigment used has a blue-red colour and the light transmitted through the glazing material has a yellow-green colour. When used in greenhouses, this glazing material has the disadvantage that portions of visible light which cannot be utilized by the plant are transmitted and, on the other hand, the red portion of visible light which can be utilized by the plant is screened off by said glazing material. Furthermore, the transmitted green portion has the additional disadvantage that it contributes to heating of the greenhouse by virtue of its conversion into long wave light.

EP-A 0,428,937 describes a grey-white coating composition for greenhouses consisting of a polymer substrate and reflecting particles suspended therein. These particles are aluminium platelets or mica platelets coated with titanium dioxide. The coating composition is used for temporary coatings in extreme weather conditions (summer). In winter, it can again be removed by washing it off with a water jet. More details regarding the pigment used are not given.

The coating composition has the disadvantage that not only the IR beams but also a substantial portion of the visible light which can be utilized by the plant are reflected by the metal particles. The green portion of the transmitted light cannot be utilized by the plant and contributes to heating of the greenhouse.

EP-A-03 98 243 describes polymeric mulch sheets and mulch films for use in agriculture which have a green absorption colour and contain a UV stabilizer. The green sheets and films absorb a large part of the solar radiation which promotes photosynthesis and plant development (PAR), and transmits enough solar radiation so as to heat the soil beneath such films and sheets. Such mulch films and sheets reduce weed growth but they have the disadvantage that the photosynthetically active radiation is absorbed and is lost for the useful plant.

35

- 4 -

L.M. Mortensen and E. Stromme describe in *Scientia Horticulturae* 33 (1987), 27-36 the effects of light quality on some greenhouse crops. Different light qualities were established in growth chambers placed outdoors by selective screening of the natural light spectrum in the chambers. The PAR level was the same at all light qualities. Blue light containing a high red/far-red ratio reduced the dry weight compared to natural (N), green, yellow and red light in chrysanthemum, tomato and lettuce. Plant height in chrysanthemum and tomato was strongly reduced by blue compared to N light, and strongly increased by green and yellow light.

WO 94/05727 discloses a composite material for the selective screening of radiation comprising a polymer and an interference pigment. The composite material can be employed in form of films, sheets and webs as covering for greenhouses, for the influencing of plant morphogenesis and for mulching purposes.

Surprisingly, it has been found that a multilayer reflective polymeric body of at least first and second diverse generally transparent polymeric materials, arranged in a sufficient member of alternating layers of said first and second polymeric materials such that a definite part of the light incident on said body is reflected wherein said first and second polymeric materials differ from each other in refractive index by at least about 0.03 can be employed for the screening of solar radiation with the aim of influencing plant growth and the morphogenesis.

The polymeric body can be used in the form of a film, sheet or web.

Multilayer reflective polymeric bodies and their manufacture are well known and described in US patents Nos. 2 408 398, 2 790 202, 2 820 249, 2 902 754, 3 024 494, 3 147 515, 3 308 508, 5 217 794 and 5 234 729 and in *Polymer Engineering and Science* 1969, Vol. 9, No. 6, pages 400-404 under the title "Physical Optics of Iridescent Multilayered Plastic Films" by T. Alfrey, E.F. Gurnee and W.J. Schrenk, in a brochure of The Dow Chemical Company titled "Coextrusion of Blown Multilayer Plastic Films" by J. Schrenk and T. Alfrey, and in *Journal of Plastic Film & Sheeting* 1994, Vol. 10, pages 78-79 by J.A. Wheatley and W.J. Schrenk.

- 5 -

5 Normally, said polymeric body has an iridescent or silvery appearance but by keeping definite tolerances of the layer thickness of about 5 nm it is possible to reflect a definite part of the light incident on the body. In this case the polymeric body appears in a definite color in the reflected light and in the complementary color in the transmitted light.

10 By variation of layer thickness, number of the alternating layers and the polymeric material the desired color can be adjusted. That means the reflecting band can intentionally be shifted in the spectrum of the sunlight.

15 The polymeric material used for the preparation of the composite materials are transparent materials like polyolefins, co- or terpolymers, for example low-density polyethylene (LDPE), vinylester copolymers like ethylene-vinylacetate copolymer (EVA), fluoropolymers, co- or terpolymers and polyvinylidene chloride (PVDC), polyvinyl chloride (PVC), polycarbonate (PC), polymethylacrylate (PMMA), polystyrene (PS), polyesters (PET, PBTE) or mixtures of transparent polymers. The term "polymer" may include mixtures of polymers.

20 The polymeric material has to be choosen so that the difference in refractive index is bigger than .03.

25 The term multilayer reflective polymeric body includes noncontinuous layers of films, such as lamellar or particulate structures incorporated into a polymer matrix.

30 The protective skin layer improves the mechanical, optical and application properties such as weather resistance, UV stability, and non-drop behavior.

35 The number of alternating layers of the polymeric body can be varied between 30 and 3000, preferably between 50 and 1000. The total number of layers for the desired effect depends on the difference of refractive indices. The smaller the difference the higher the total number of layers.

- 6 -

The entire disclosure of all applications, patents and publications, cited above and below are hereby incorporated by reference.

5 In order that the invention may be more readily understood, reference is made to the following example, which is intended to be illustrative of the invention, but is not intended to be limiting in scope.

Example 1

10 Fig. 1 shows the reflectance spectrum of a polymeric multilayer film which consists of alternating layers of polycarbonate (PC refractive index $n_D = 1,587$) and polymethacrylate (PMMA, $n_D = 1,491$). The total numbers of layers is 100 and the layer thickness is 100 nm for a PC layer resp. 140 nm for PMMA layer.

15 The spectrum shows that the film is transparent below 700 nm and reflects with a maximum around 740 nm.

20 This film therefore is suitable for influencing of the growth of plants, such as vegetables and tomatoes, so that this plants become more compact. The background for this photomorphogenetic effect is the change of the red to far red ratio for the phytochrome.

Example 2

25 Fig. 2 shows the refractive spectrum of a polymeric multilayer film which consists of alternating layers of PC and PMMA. The total number of layers is 100 and the layer thickness is 100 nm for a PC layer resp. 115 nm for PMMA layer.

30 This film is transparent below 620 nm and above 700 nm and shows reflection inbetween. This film is suitable for influencing the growth of plants, when slender plants are desired, such as for roses.

35 The background here is the opposite effect of Example 1.

- 7 -

Example 3

Fig. 3 shows the reflective spectrum of a polymeric multilayer film which consists of alternating layers of PC and PMMA. The total numbers of layers is 50 and the layer thickness is 70 nm for PC resp. 105 nm for PMMA. This film reflects the green light around 540 nm that cannot be utilized for the growth of plants (minimum of PAR). It is therefore suitable for greenhouse films.

Example 4

Fig. 4 shows the reflective spectrum of a polymeric multilayer film which consists of alternating layers of PC and PMMA. The total number of layers is 500 and the layer thickness is $(70 + 0.05 n)$ nm for PC and $(75 + 0.0533 n)$ nm for PMMA, n indicating the number of layer.

This spectrum is similar to the reflection spectrum in T. Alfrey, jr. et al. Polym. Eng. Sci. 9 (1969), 400-404. This film reflects nearly the total PAR spectrum and therefore suitable for mulch foils.

- 8 -

Claims

1. A multilayer reflective polymeric body of at least first and second diverse generally transparent polymeric materials, arranged in a sufficient member of alternating layers of said first and second polymeric materials such that a definite part of the light incident on said body is reflected, wherein said first and second polymeric materials differ from each other in refractive index by at least about 0.03 for the screening of solar radiation with the aim of influencing plant growth and the morphogenesis.
2. The multilayer reflective polymeric body of claim 1 wherein said polymeric body is in the form of a film, sheet or web.
3. The multilayer reflective polymeric body of claim 1 wherein said polymeric body includes a protective skin layer on at least one major surface thereof.
4. The multilayer reflective polymeric body of claims 1 to 3 wherein said protective skin layer contains pigments, dyes, fillers, antidrop agents and functional additives and processing aids necessary for the particular polymer.

1/4




FIG. 1

2/4




FIG. 2

3/4




FIG. 3

6/6




FIG. 4

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/EP 95/02786

A. CLASSIFICATION OF SUBJECT MATTER

A 01 G 13/02

According to International Patent Classification (IPC) or to both national classification and IPC ⁶

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

A 01 G, B 32 B, C 08 J, C 08 K, C 09 D, G 02 B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP, A, 0 298 942 (TEN0 AB) 11 January 1989 (11.01.89), claims 5,8,9; fig. 4; abstract.	1-4
A	EP, A, 0 455 942 (CARL FREUDENBERG) 13 November 1991 (13.11.91), abstract.	1,2,4
A	WO, A, 86/07 235 (GRAVISSE) 18 December 1986 (18.12.86), abstract.	1,2
A	US, A, 4 920 692 (KITAMURA et al.) 01 May 1990 (01.05.90),	1-4

☒ Further documents are listed in the continuation of box C.☐ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search
17 October 1995

Date of mailing of the international search report

23.11.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

RIEMANN e.h.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 95/02786

C(Czechoslovakia) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to class No.
	abstract; claims. --	
A	EP, A, 0 398 243 (GINEGAR PLASTIC PRODUCTS) 22 November 1990 (22.11.90), the whole document (cited in the application). --	1-4
A	WO, A, 94/05 727 (HYPLAST N.V.) 17 March 1994 (17.03.94), abstract; claims (cited in the application). --	1-4
A	EP, A, 0 428 937 (STATE OF ISRAEL MINISTRY OF DEFENCE) 29 May 1991 (29.05.91), abstract; claims (cited in the application). --	1, 4
A	DE, A, 2 544 245 (RÖHM GMBH) 14 April 1977 (14.04.77), the whole document (cited in the application). --	1-4
A	US, A, 3 147 515 (DONALD L. AMSDEN) 08 September 1964 (08.09.64), the whole document (cited in the application). ----	1

ANHANG

ANNEX

ANNEXE

zum internationalen Recherchen-
bericht über die internationale
Patentanzmeldung Nr.

to the International Search
Report to the International Patent
Application No.

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/EP 95/02786 SAE 114401

In diesem Anhang sind die Mitglieder
der Patentfamilien der in obenge-
nannten internationalen Recherchenbericht
angeführten Patentedokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visé ci-dessus. Les renseigne-
ments fournis sont énoncés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

In Recherchenbericht angeführtes Patentedokument in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
EP A1 298942	11-01-89	SE A0 8702819 SE A 8702819	09-07-87 10-01-89
EP A2 455942	13-11-91	AT E 110223 DE A1 4014717 DE C0 4014717 DE C0 59102606 DE A0 4555942 DE B1 4555942 ES T0 20558949	15-09-94 14-11-91 19-11-92 29-09-94 23-04-92 24-08-94 01-11-94
WO A1 8607235	18-12-86	DE C0 3678800 DE A1 3324524 DE B1 3324524 DE A1 3324524 DE B1 3324524 JP T2 63500213	23-05-91 10-06-87 17-04-91 05-12-86 29-06-90 28-01-88
US A 4920692	01-05-90	JP A2 62265927 JP B4 40088944 AU A1 68288787 AU B2 596697 CN A 87100888 CN A 1009799 DE C0 3767402 DE A1 3356301 DE B1 3356301 SG B1 93006683 SG A 363791	18-11-87 18-09-92 11-03-88 10-05-90 17-02-88 03-10-90 21-03-91 24-02-88 16-01-91 23-01-95 21-06-91
EP A1 398243	22-11-90	IL A0 90321 US A 5138792	15-12-89 18-08-92
WO A2 9405727	17-03-94	CN A 1083829 DE A1 42300023 EP A1 6559198 FI A 951074 FI A0 951074 IL A0 106759 WO A3 9405727 NL A 9201568	16-03-94 17-03-94 28-06-94 08-03-95 08-03-95 08-12-94 09-06-94 05-04-94
EP A1 428937	29-05-91	AU A1 66692790 CA AA 2029941 IL A0 92372 ZA A 9009177	23-05-91 21-05-91 26-07-90 25-09-91
DE A1 2544245	14-04-77	AT A 5157776 AT B 3597220 CA A1 10852055 DE B2 2544245 DE C0 2544245 FR A1 3326549 FR B1 3326549 IT A 1069666 NL A 7610913 US A 4090770	15-04-80 25-11-80 09-09-80 30-04-81 17-12-81 29-04-77 29-06-82 05-03-85 05-04-77 23-05-78
US A 3147515		keine - none - rien	